


## PEE & PEI TYPE CORES



### PEE & PEI TYPE CORES (MATERIALS):P1,P2,P3

#### Dimensions

CORES TYPE	Dimensions(mm)						
	A	B	C	D	E	F	I
PEE14	14.00±0.30	3.50±0.10	5.00±0.10	3.00±0.05	10.50min	2.00±0.10	
PEI 14	14.00±0.30	3.50±0.10	5.00±0.10	3.00±0.05	10.50min	2.00±0.10	1.50±0.1
PEE18	18.00±0.30	4.00±0.10	10.00±0.20	4.00±0.10	14.00±0.30	2.00±0.10	
PEI 18	18.00±0.30	4.00±0.10	10.00±0.20	4.00±0.10	14.00±0.30	2.00±0.10	2.00±0.1
PEE22	21.80±0.40	5.70±0.10	15.80±0.50	5.00±0.10	16.80±0.4	3.20±0.10	
PEI 22	21.80±0.40	5.70±0.10	15.80±0.50	5.00±0.10	16.80±0.4	3.20±0.10	2.50±0.1
PEE32	31.75±0.64	6.35±0.13	20.32±0.41	6.35±0.13	24.9min	3.18±0.20	
PEI 32	31.75±0.64	6.35±0.13	20.32±0.41	6.35±0.13	24.9min	3.18±0.20	3.18±0.13
PEE38	38.10±0.76	8.26±0.13	25.40±0.51	7.62±0.15	30.23min	4.45±0.13	
PEI 38	38.10±0.76	8.26±0.13	25.40±0.51	7.62±0.15	30.23min	4.45±0.13	3.81±0.13
PEE43	43.20±0.90	9.53±0.13	27.90±0.60	8.10±0.20	34.7min	5.40±0.13	
PEI 43	43.20±0.90	9.53±0.13	27.90±0.60	8.10±0.20	34.7min	5.40±0.13	4.06±0.12

#### Effective parameter

CORES TYPE	Effective parameter					
	C1(mm <sup>-1</sup> )	Le	Ae	Ve	Wt(g/set)	AL±25% $\mu$ H/N <sup>2</sup>
PEE14	1.43	20.7	14.5	300	1.40	1200(P3)
PEI 14	1.6	16.7	14.5	240	1.27	1105(P3)
PEE18	0.616	24.3	39.5	960	4.80	2520(P3)
PEI 18	0.498	20.3	40.8	830	4.29	2851(P3)
PEE22	0.414	32.5	78.5	2550	13.00	4040(P3)
PEI 22	0.332	26.1	75.5	2040	11.42	4880(P3)
PEE32	0.315	41.4	130	5380	26.00	5673(P3)
PEI 32	0.27	35.1	130	4560	22.00	6422(P3)
PEE38	0.27	52.4	194	10200	50.90	7006(P3)
PEI 38	0.225	43.7	194	8460	42.50	8132(P3)
PEE43	0.267	61.1	229	18900	70.60	7292(P3)
PEI 43	0.220	50.4	229	11500	58.00	8525(P3)